

CURVA GRANULOMÉTRICA

DATOS DE LA MUESTRA

SITIO:	Arenera Helena - Río Cuarto		
Muestra Nro.:	Tamiz 12	Prof.:	

TIPO DE TAMIZADO	EN SECO	Peso muestra	264.9 g
------------------	---------	--------------	---------

Tamiz Nro						4	10	20	40	200
Abertura (mm)	0	0	0	0	0	4.75	2	0.85	0.425	0.075
% Pasante	0.0	0.0	0.0	0.0	0.0	100.0	19.9	0.1	0.04	0.0
% Retenido acumulado						0.0	80.1	99.9	100.0	100.0
% Retenido parcial						0.0	80.1	19.8	0.0	0.0

Pasa tamiz N° 4 (4,75 mm):	100.0 %	Fracciones presentes % en peso	
Pasa tamiz N° 10 (2.0 mm):	19.9 %		
Pasa tamiz N° 40 (0,425 mm):	0.0 %		
Pasa tamiz N° 200 (0,075 mm):	0.0 %		
D ₆₀ :	3.08 mm		
D ₃₀ :	2.23 mm	Grava gruesa (> 19 mm):	%
D ₁₀ (talla efectiva):	1.30 mm	Grava fina (19 - 4.75 mm):	0.0 %
Coefficiente de uniformidad (Cu):	2.4	Arena gruesa (4.75 - 2 mm):	80.1 %
Grado de curvatura (Cc):	1.2	Arena media (2 - 0.425 mm):	19.9 %
		Arena fina (0.424 - 0.075 mm):	0.0 %
		Limo y arcilla (< 0.075 mm):	0.0 %

CLASIFICACIÓN UNIFICADA: SP

